




Blue 385
 CI Pigment Blue 28
 Cobalt Aluminate Blue
 Spinel

A rich blue powder produced by high temperature calcination. This pigment has fair UV and visible opacity, is chemically inert, heat resistant, and stable to ultraviolet light. It is non-bleeding and non-migratory. It has exceptional durability, and is generally used in applications where resistance to heat, light, and weather are needed. It is compatible with most resin systems and polymers, and is non-warping.

[Product Information](#)

Reflectance

— Masstone



[Visible Only](#) [300-2500 nm](#)

Revision Date:	Apr-01-2002
Specific Gravity	4.2
Oil Absorption	30 kg/100 kg
Residue 325 mesh [44 µm]	0.01 wt%
Average Particle Size	0.4 µm
pH	10
Heat Stability	1260 °C
Surface Area BET	15.5 m ² /g
Conductivity	350 µS/cm
Percent Moisture	0.6 wt%
Crystal Structure	spinel x-ray
Lightfastness	8 (1-8)
Weatherability	5 (1-5)
Acid Resistance	5 (1-5)
Alkali Resistance	5 (1-5)
Bulk Density	0.43 kg/L